

Topcoats (see footnotes)	VOC (g/l)	A/D FIREFILM III	A/D FIREFILM III C	THERMO-SORB	Nullifire S605	Nullifire S606	THERMO-LAG 3000 2000, 440
A/D Colorcoat	300	Acceptable (1,2)	Acceptable (1,2,4)	Acceptable (2)			
Carbocoat 30R	300	Acceptable (2)	Acceptable (2,4)	Acceptable (2)			
Carbocoat 8215 VOC	336	Acceptable (2)	Acceptable (2,4)				Acceptable (2,4)
Carbothane 133 HB	383			Acceptable (2)		Acceptable (2)	
Carbothane 133 LH	324			Acceptable (2)			
Carbothane 133 VOC	157					Acceptable (2)	
Carbothane 133 MC	97	Acceptable (2)	Acceptable (2,4)	Acceptable (2)		Acceptable (2)	
Carbothane 134 WB	95	Acceptable (2)	Acceptable (2,4)				
Sanitile 155	250	Acceptable (1,2)	Acceptable (1,2)	Acceptable (1,2)			
Sanitile 655	335			Acceptable (1,2)			
Carbocrylic 3350	250	Acceptable (1,2)	Acceptable (1,2)	Acceptable (1,2)			
Carbocrylic 3359	132			Acceptable (2)			
Carbocrylic 3359 DTM	217			Acceptable (2)			
Carbocrylic 3359 DTMC	100			Acceptable (2)		Acceptable (2)	
Carboguard 1340 Carbothane 133HB	95 383			Acceptable (1,2)	Acceptable (1,2,3)	Acceptable (1,2)	Acceptable (1,2,3)
Carboguard 1340 Carbothane 133 VOC	95 157				Acceptable (1,2,3)	Acceptable (1,2)	
Carboguard 1340 Carbothane 133 MC	95 97				Acceptable (1,2,3)	Acceptable (1,2)	Acceptable (1,2,3)
Carboguard 1340 Carbocrylic 3359	95 132					Acceptable (1,2)	
Carboguard 889	276						Acceptable (1,2,3)
Carbomastic 94	120						Acceptable (1,2,3)
Carboguard 890 VOC	100	Acceptable (2)	Acceptable (2)	Acceptable (2)		Acceptable (2)	
Carboguard 893 SG	336			Acceptable (1,2)			
Rustbond Carbothane 133 HB	85 383				Acceptable (1,2,3)	Acceptable (1,2)	
Rustbond Carbothane 133 VOC	85 157				Acceptable (1,2,3)	Acceptable (1,2)	
Rustbond Carbothane 133 MC	85 97				Acceptable (1,2,3)	Acceptable (1,2)	
Rustbond Carbocrylic 3359	85 132					Acceptable (1,2)	

Note: All water based topcoats used with AD Firefilm III and A/D Firefilm III C must be spray applied.

1 - General Purpose - exposed to temperature and humidity fluctuations during changing construction conditions

2 - Interior Conditioned Space - fireproofing is under constant heat; temperature and humidity do not fluctuate

3 - Exterior ratings- exposed to the elements

4 - Designates topcoats tested for clean room applications - Consult Carboline Technical Service for specific details prior to application