

SELECTION & SPECIFICATION DATA

Generic Type	High solids epoxy polyamide
Description	A 1:1, high solids polyamide epoxy designed to provide very good corrosion resistance as a single coat, direct-to-metal (DTM) exterior coating for railcars and other structures. When all epoxies will chalk and yellow under UV exposure, this coating has good color and gloss retention better retention better than most.
Features	<ul style="list-style-type: none"> • Single coat direct to metal high solids epoxy • Low VOC & HAPS • Easy one coat high build coverage • Excellent adhesion • Very good resistance to corrosion and spillage /splash of mild chemicals
Color	Black, Grey, and White or per customer requirements
Gloss	60-80 gloss units per customer requirements (ASTM D523 @ 60° angle)
Dry Film Thickness	4 - 6 mils (102 - 152 microns) per coat Do not exceed 12 mils (300 microns)
Solids Content	By Volume 73% +/- 3%
Theoretical Coverage Rate	1171 ft ² /gal at 1.0 mils (28.7 m ² /l at 25 microns) 293 ft ² /gal at 4.0 mils (7.2 m ² /l at 100 microns) 195 ft ² /gal at 6.0 mils (4.8 m ² /l at 150 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : Per EPA Method: 1.8 lbs / gal (216 g/l) These are nominal values and may vary slightly with color.

SUBSTRATES & SURFACE PREPARATION

Steel	Severe service applications – blasted to SSPC-SP-10 to a 1.5-2.5 mil angular profile Lesser service applications – blasted to SSPC-SP-6 Surface to be free of all looser rust, dirt, grease and other contaminants
Aluminum	Remove all surface contaminants and treat with Strathmore's Wash Primer or equivalent

PERFORMANCE DATA

Test Method	Results
Adhesion (ASTM D3359)	5A
Conical Mandrel (ASTM D522)	Passes 1/8"
Hardness (ASTM D3363)	4H-5H
Impact Resistance (ASTM D2794)	Up to 120 lbs.in (Direct) and 60 lbs.in (Rev)
QUV Resistance (ASTM D2794)	Gray chalk 19°, 320 hrs- QUV UVA-340 Bulb

Chemical Resistance: No effect on film on various chemicals on 4 hrs and 8 hrs spot tests.

MIXING & THINNING

- Mixing**
 - Agitate thoroughly each component before combining
 - Mix (combine) 1:1 by volume Part A and Part B
 - Agitate thoroughly again after combining
 - If necessary reduce up to 15% after combining components
- Thinning**
 - 5-15% by volume maximum
 - Consult Carboline for recommendations
- Ratio**
 - 1 Part A to 1 Part B
 - Allow 20 minutes @ 75°F (23°C) of induction time to attain maximum gloss
- Pot Life**
 - 6 hours @ 70°F (21°C)

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

- Airless Spray**
 - 45:1 Airless spray equipment
 - Tip Size: 0.017 to 0.021
 - Pump Pressure: 2500-3500 psi (17-24 MPa)
 - To minimize or eliminate thinner use in-line heated equipment with insulated hoses to reach application vis. Do not exceed 165°F (74°C).

APPLICATION PROCEDURES

- General** | Designed to be applied direct to metal in a single or two coat application.

APPLICATION CONDITIONS

Condition

Must be a minimum of 5°F (3°C) above the dew point during the surface preparation and coating application.

CURING SCHEDULE

Surface Temp.	Dry to Handle	Dry to Touch	Minimum Recoat Time	Maximum Recoat Time
70°F (21°C)	5 Hours	3 Hours	NR	NR
72°F (22°C)	NR	NR	12 Hours	7 Days

- Force Cure** | If car is force dried, 1 hr minimum air dry @ 75°F (23°C) before oven. Then force dry @ 145°F (60°C) for 1 hour, adjusting for ambient maximum conditions.

CLEANUP & SAFETY

- Cleanup** | MEK may be used for clean up. Batch mixed material will set up in the lines and equipment if left overnight. With plural component equipment, be sure to flush from the mixing head through the delivery hose and guns.

CLEANUP & SAFETY

Safety	Handle with care. Before and during use, observe all safety labels on packaging and paint containers and follow all caution statements on this product data sheet. Consult the Safety Data Sheet (SDS) for this product and follow all local or national safety regulations. Employ normal workmanlike safety precautions.
Ventilation	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to ensure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.

PACKAGING, HANDLING & STORAGE

Packaging	55 gal drums or 5 gal pails
Shelf Life	Generally one year from date of manufacturing When kept at recommended storage conditions at 70°F (21°C) and in original unopened containers. Do not use material beyond shelf life.
Storage Temperature & Humidity	Recommended storage at 70°F (21°C) Do not store at temperatures above 100°F (38°C)
Storage	Containers must be closed tightly. Do not store outside. Rotate stock.
Flash Point (Setaflash)	Part A: 43°F (6°C) Part B: 44°F (7°C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.