

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	5:1, high solids, two component, polyurethane color coat coating
<b>Description</b>	A 5:1, high solids, two component, polyurethane color coat coating. This coating is designed to provide very good corrosion, UV and chemical resistance as a middle coat, used with a primer and a clearcoat.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Excellent Weathering resistance</li> <li>• Very Low HAPS</li> <li>• Low VOC</li> <li>• Easy one coat coverage</li> <li>• Excellent adhesion</li> <li>• Very good resistance to corrosion and spillage /splash of mild chemical</li> <li>• Very flexible</li> <li>• Excellent color fastness</li> </ul>
<b>Color</b>	Black or per customer requirements
<b>Gloss</b>	20-25°+ (ASTM D523 @ 60° angle)
<b>Dry Film Thickness</b>	2 - 4 mils (51 - 102 microns) per coat Not to exceed 8 mils (200 µm) DFT.
<b>Solids Content</b>	By Volume 50% +/- 3%
<b>Theoretical Coverage Rate</b>	802 ft <sup>2</sup> /gal at 1.0 mils (19.7 m <sup>2</sup> /l at 25 microns) 401 ft <sup>2</sup> /gal at 2.0 mils (9.8 m <sup>2</sup> /l at 50 microns) 200 ft <sup>2</sup> /gal at 4.0 mils (4.9 m <sup>2</sup> /l at 100 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : Per EPA Method 24: 2.03 lbs/gal (243 g/l) These are nominal values and may vary slightly with color.

## SUBSTRATES & SURFACE PREPARATION

<b>Steel</b>	Blasted to SSPC-SP-10 to a 1.5-2.5 mil angular profile Lesser service applications – blasted to SSPC-SP-6 Surface to be free of all looser rust, dirt, grease and other contaminants
<b>Aluminum</b>	Remove all surface contaminants and treat with Strathmore's Wash Primer or equivalent.

# Railplex LV Colorcoat

## PRODUCT DATA SHEET



### PERFORMANCE DATA

Test Method	Results
Adhesion (ASTM D3359)	5A
Conical Mandrel (ASTM D522)	Passes 1/8"
Hardness (ASTM D3363)	H
Impact Resistance (ASTM D2794)	Up to 160 lbs. in (Direct) and 160 lbs. in (Rev)

**QUV Resistance (ASTM G154):** 4000 hours UVA-340

**Chemical Resistance:** No effect on film in various chemicals on 4 hrs/8hrs spot tests

**Corrosion Resistance (ASTM B117):** 1500 hours salt fog over recommended primer

### MIXING & THINNING

<b>Mixing</b>	Agitate thoroughly each component before combining Mix (combine) 5:1 by volume Part A and Part B Agitate thoroughly again after combining If necessary, reduce up to 15% after combining components
<b>Thinning</b>	None required, consult Carboline for recommendations
<b>Ratio</b>	5:1 Part A to Part B (by Volume)
<b>Pot Life</b>	4 hours (@70°F (21°C))

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Airless Spray</b>	<ul style="list-style-type: none"><li>• 45:1 Airless spray equipment</li><li>• Tip Size: 0.013 to 0.017</li><li>• Pump Pressure: 2500-3500 psi (17-24 MPa)</li></ul> <p>To minimize or eliminate thinner use in-line heated equipment with insulated hoses to reach application vis. Do not exceed 165°F (74°C).</p>
----------------------	--

### APPLICATION PROCEDURES

**General** | Designed to be applied in a single or two coat application.

### APPLICATION CONDITIONS

Condition
-----------

Must be a minimum of 5°F (3°C) above the dew point during the surface preparation and coating application.

### CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry to Handle	Minimum Recoat Time	Maximum Recoat Time
70°F (21°C)	2 Hours	4 Hours	NR	NR
72°F (22°C)	NR	NR	8 Hours	5 Days

---

**CURING SCHEDULE**

---

**Force Cure** | If car is force dried, 1 hr minimum air dry @ 75°F (23°C) before oven. Then force dry @ 145°F (60°C) for 1 hour, adjusting for ambient maximum conditions

---

**CLEANUP & SAFETY**

---

**Cleanup** | MEK may be used for clean up. Batch mixed material will set up in the lines and equipment if left overnight. With plural component equipment, be sure to flush from the mixing head through the delivery hose and guns.

**Safety** | Handle with care. Before and during use, observe all safety labels on packaging and paint containers and follow all caution statements on this product data sheet. Consult the Safety Data Sheet (SDS) for this product and follow all local or national safety regulations. Employ normal workmanlike safety precautions.

**Ventilation** | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to ensure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.

---

**PACKAGING, HANDLING & STORAGE**

---

**Packaging** | 55 gal drums or 5 gal pails

**Shelf Life** | Generally one year from date of manufacturing when kept at recommended storage conditions at 70°F (21°C) and in original unopened containers.

Do not use material beyond shelf life.

**Storage Temperature & Humidity** | Do not store at temperatures above 100°F (38°C).

**Storage** | Containers must be closed tightly. Do not store outside. Rotate stock.

---

**WARRANTY**

---

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.