
SELECTION & SPECIFICATION DATA

Generic Type	Alkyd Phenolic
Description	A dipping primer that provides good flexibility, oil and corrosion resistance for use on industrial metal applications.
Color	Brown (0200)
Finish	Flat
Dry Film Thickness	1 - 1.5 mils (25 - 38 microns) per coat
Solids Content	By Volume 24% +/- 2%
Theoretical Coverage Rate	385 ft ² /gal at 1.0 mils (9.4 m ² /l at 25 microns) 257 ft ² /gal at 1.5 mils (6.3 m ² /l at 38 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 5.51 lbs / gal (660 g/l)

MIXING & THINNING

Thinning | Can be applied as received and further reduction should not be necessary.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General | Dip

CURING SCHEDULE

Surface Temp.	Dry Hard	Dry to Recoat	Tack Free
72°F (22°C)	4 Hours	4 Hours	2 Hours

Dust Free: 30 minutes at 72°F (22°C)

CLEANUP & SAFETY

Cleanup | Clean up application equipment with solvent flush, such as MPK or butyl acetate while product is still wet.

PACKAGING, HANDLING & STORAGE

Storage Temperature & Humidity | This product should not be stored below 40°F (4°C) and not above 110°F (43°C).

Storage | Product should be stored in sealed containers when not in use. Do not store containers near sources of heat.

Storage | Handling should be done in accordance to local, state and Federal safety regulations. Disposal should be done in accordance to local, state and Federal regulations. Please consult the specific Safety Data Sheets for more specific handling and disposal information.

Strathmore 3321 Alkyd Primer

PRODUCT DATA SHEET



PACKAGING, HANDLING & STORAGE

Flash Point (Setaflash) | 81°F (27°C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.