
SELECTION & SPECIFICATION DATA

Generic Type	Aluminum Alkyd Coating
Color	Aluminum
Gloss	Metallic
Wet Film Thickness	3.0 mils single coat
Dry Film Thickness	0.5 mils (13 microns) single coat
Solids Content	By Volume 22% Solids by Weight: 26.6%
Theoretical Coverage Rate	719 ft ² /gal at 0.5 mils (17.6 m ² /l at 12 microns) 359 ft ² /gal at 1.0 mils (8.8 m ² /l at 25 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 3.22 lbs/gal (385 g/l) Actual Solvent Content/Gal: 1.32 lbs (158 g/l)
Viscosity	#4 Zahn: 24-28 sec Viscosity (reduced): #1 Zahn - 45-50 sec

MIXING & THINNING

Mixing	Power mix until uniform in consistency. Avoid excessive air entrapment.
Thinning	May be reduced with water at 5:2 ratio (paint: water)

APPLICATION PROCEDURES

General | Dip

PACKAGING, HANDLING & STORAGE

Shipping Weight (Approximate)	8.52 lbs/gal (1.02 kg/l)
Flash Point (Setaflash)	105°F (41°C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.