

SELECTION & SPECIFICATION DATA

Generic Type	A two component, high solids, modified epoxy formulated for use as a primer
Description	A two component, high solids, modified epoxy formulated for use as a primer in conjunction with Stratholiner 7150 and 7200, to form a protective lining system with excellent resistance to acetic and hydrochloric acids. Typical use will be a tank car lining system for acetic and hydrochloric acids as well as dry bulk hopper cars with residual process acids.
Features	<ul style="list-style-type: none"> • Excellent resistance to acetic and hydrochloric acids • High solids • Very low water vapor transmission rate
Color	Red Brown or per customer requirements
Dry Film Thickness	4 - 6 mils (102 - 152 microns) single coat
Solids Content	By Volume 57% +/- 2%
Theoretical Coverage Rate	<p>914 ft²/gal at 1.0 mils (22.4 m²/l at 25 microns)</p> <p>229 ft²/gal at 4.0 mils (5.6 m²/l at 100 microns)</p> <p>152 ft²/gal at 6.0 mils (3.7 m²/l at 150 microns)</p> <p>Allow for loss in mixing and application.</p>
VOC Values	<p>As Supplied : Per EPA Method: 3.03 lbs/gal (363 g/l)</p> <p>Thinner 10 : 3.23 lbs/gal (387 g/l) max</p> <p>These are nominal values and may vary slightly with color.</p>
Dry Temp. Resistance	Continuous: 225°F (107°C)

SUBSTRATES & SURFACE PREPARATION

Steel	Blast to NACE #2 / SSPC 10, Near White Metal and a profile of 2.5 – 3.0 mils (64 – 76 µm). Surface to be free of all loose rust, dirt, grease and other contaminants.
Aluminum	Remove all surface contaminants and treat with Strathmore's Wash Primer or equivalent

PERFORMANCE DATA

Test Method	System	Results
Abrasion Resistance (ASTM D4060)	Stratholiner 7100 / Stratholiner 7150; Stratholiner 7100 / Stratholiner 7200	CS17 wheel, 1kg load, 1000 cycles; 50 mg loss
Adhesion (ASTM D4541)	Stratholiner 7100 / Stratholiner 7150; Stratholiner 7100 / Stratholiner 7200	1800 psi
Hardness (ASTM D3363)	Stratholiner 7100 / Stratholiner 7150; Stratholiner 7100 / Stratholiner 7200	4H
Salt Spray (ASTM B117)	Stratholiner 7100 / Stratholiner 7150; Stratholiner 7100 / Stratholiner 7200	2000+ hours
Thermal Shock Resistance	Stratholiner 7100 / Stratholiner 7150; Stratholiner 7100 / Stratholiner 7200	10 cycles water 33°F to 200°F (0°C to 93°C)

Chemical Resistance: Process acids in plastic pellets and granules

Stratholiner 7100

PRODUCT DATA SHEET



MIXING & THINNING

Mixing	For hand mixing of touch up or repair kits, if necessary. Agitate thoroughly each component before combining. Agitate thoroughly again after combining.
Thinning	0-5% by volume maximum, consult Carboline for recommendations
Ratio	1:1 Part A to Part B, by volume
Pot Life	4 hours @ 77°F (25°C) Caution: Pot Life is significantly reduced with heat.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Plural Component	Tip Size: 0.019 to 0.025" (0.48-0.64 mm) Pump Pressure: 2800 psi (19.3 MPa) minimum Heated plural component equipment. Do not exceed 120°F (48.8°C)
-------------------------	---

APPLICATION CONDITIONS

Condition	Surface
Minimum	60°F (16°C)

Metal temperature must be a minimum of 5°F (3°C) above the dew point during the surface preparation and coating application

CURING SCHEDULE

Surface Temp.	Set Time	Tack Free	Dry Hard
77°F (25°C)	2 Hours	8 Hours	12 Hours

In Service Times: After force cure of 150°F (66°C) for 6 hours.

Force Cure	After coating application, mandatory 2-hour ambient air flash time, then overnight cure of forced air at 90-100°F (32-38°C) heat for 12 hours minimum.
-------------------	--

CLEANUP & SAFETY

Cleanup	MEK may be used for clean up. Batch mixed material will set up in the lines and equipment if left overnight. With plural component equipment, be sure to flush from the mixing head through the delivery hose and guns.
Safety	Handle with care. Before and during use, observe all safety labels on packaging and paint containers and follow all caution statements on this product data sheet. Consult the Safety Data Sheet (SDS) for this product and follow all local or national safety regulations. Employ normal workmanlike safety precautions.

CLEANUP & SAFETY

Ventilation	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to ensure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.
--------------------	--

PACKAGING, HANDLING & STORAGE

Shelf Life	Generally, one year from date of manufacturing when kept at recommended storage conditions at 70°F (21°C) and in original unopened containers. Do not use material beyond shelf life
Storage Temperature & Humidity	Do not store at temperatures above 100°F (38°C)
Storage	Containers must be closed tightly. Do not store outside. Rotate stock.
Flash Point (Setaflash)	Part A: 71°F (21.7°C) Part B: 72°F (22°C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.